



# TEST REPORT

DATE: 11-03-2020

Page 1 of 2

TEST NUMBER: 0270990

<b>CLIENT</b>	Urban Surfaces
---------------	----------------

<b>TEST METHOD CONDUCTED</b>	ASTM F3414 - 20 (CPSC) Standard Test Method for Determining Ortho-Phthalate Concentration in Flooring Containing Polyvinyl Chloride Standard Test Method for Determining Ortho-Phthalate Concentration in Flooring Containing Polyvinyl Chloride
------------------------------	---



DESCRIPTION OF TEST SAMPLE	
<b>IDENTIFICATION</b>	Glue Down LVT

## GENERAL PRINCIPLE

The submitted material was tested via CPSC-C1001-09.3 in order to determine the level of phthalate compounds present in the material. The specimen was tested in duplicate.

## TEST RESULTS

COMPOUND	RESULT
Bis (2-ethylhexyl) Phthalate (DEHP)	<1.0 ppm
Butyl Benzyl Phthalate (BBP)	<1.0 ppm
Di Isodecyl Phthalate (DIDP)	<1.0 ppm
Di Isononyl Phthalate (DINP)	<1.0 ppm
Di-N-Butyl Phthalate (DNBP)	<1.0 ppm
Di-N-Hexyl phthalate (DNHP)	<1.0 ppm
Di-N-Octylphthalate (DNOP)	<1.0 ppm
Di-N-Pentyl Phthalate (DPENP)	<1.0 ppm
Dicyclohexyl Phthalate (DCHP)	<1.0 ppm
Diisobutyl Phthalate (DIBP)	<1.0 ppm

## COMMENTS

This material **meets** the CPSIA Guidelines as specified.

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.