



TEST REPORT

DATE: 03-07-2018

Page 1 of 1

TEST NUMBER: 0244992

CLIENT	Urban Surfaces
---------------	----------------

TEST METHOD CONDUCTED	ASTM F387 Standard Test Method for Measuring Thickness of Resilient Floor Covering with Foam Layer
------------------------------	--



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Sound Tec
CONSTRUCTION	Floor Plank

GENERAL PRINCIPLE

The total thickness of a resilient flooring material is determined through measurements made using a .250 inch presser foot and a dial micrometer. The average of 5 total measurements is reported as the average total thickness.

TEST RESULTS

	THICKNESS
SPECIMEN 1	0.249 Inch
SPECIMEN 2	0.250 Inch
SPECIMEN 3	0.248 Inch
SPECIMEN 4	0.249 Inch
SPECIMEN 5	0.250 Inch

AVERAGE TOTAL THICKNESS	0.249 Inch
--------------------------------	------------

CORE	PAD	VINYL
0.156 Inch	0.071 Inch	0.022 Inch

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.