



TEST REPORT

DATE: 01-11-2018

Page 1 of 1

TEST NUMBER: 0243052

CLIENT	Urban Surfaces
TEST METHOD CONDUCTED	ASTM F925 (Regular) Standard Test Method for Resistance to Chemicals of Resilient Flooring
DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Alamo Click
CONSTRUCTION	Floating Floor Plank

TEST RESULTS

5 MINUTE RATINGS	24 HOUR RATINGS
------------------	-----------------

STAINING AGENT	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE
5% Acetic Acid	0	0	0	0	0	0
70% Isopropyl Alcohol	0	0	0	0	0	0
Mineral Oil	0	0	0	0	0	0
5% Sodium Hydroxide	0	0	0	0	0	0
5% Hydrochloric Acid	0	0	0	0	0	0
5% Ammonia	0	0	0	0	0	0
Bleach	0	0	0	0	0	0
5% Phenol	0	0	0	0	0	0
Gasoline	0	0	0	0	0	0
Sulfuric Acid	0	0	0	0	0	0
Kerosene	0	0	0	0	0	0
Olive Oil	0	0	0	0	0	0

RATING KEY
0 - No change (----)
1 - Slight change
2 - Moderate change
3 - Severe change

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.